

GardaPat 13 BIANKA

Description:

Garda 2 side coated woodfree paper, pure white shade, with a matt surface and high bulk (volume 1.3).

Thanks to advanced technology, it is able to combine high thickness (volume 1.3, 40% higher than any other traditional matt paper at the same substance) with a velvet surface.

GardaPat is available in three versions: KLASSICA (warm natural shade), KIARA (natural white shade) and BIANKA (pure white shade). Suitable and tested on leading digital inkjet presses.

Available in a wide range of substances and formats, in sheets and reels.

End uses:

Books, Brochures, Catalogues, Covers, Direct mail, Folders, Inserts, Packaging, Postcards

Print methods:

Flexo, Offset, Inkjet

Certificates:

- [HP Indigo GardaPat13Bianka 115gsm](#)
- [HP Indigo GardaPat13Bianka 135gsm](#)
- [HP Indigo GardaPat13Bianka 150gsm](#)
- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [Paper Profile Garda](#)
- [Paper Profile GardaRecycled Print](#)
- [Paper Profile Creator - Cartiere del Garda](#)
- [REACH regulation Lecta](#)
- [ISO 14001 Environment](#)
- [EMAS Cartiere del Garda mill](#)
- [ISO 50001 Energy Efficiency](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)

For applications that require specific certifications or approvals, please contact our sales teams.

GardaPat 13 BIANKA

Technical specifications

Property	Test Method	Unit	Tolerance	115	135	150
Substance	ISO 536 TAPPI T410	g/m ²	±4%	115	135	150
Thickness	ISO 534 TAPPI T411	µm	±4%	149	175	195
Thickness (pt.)	ISO 534 TAPPI T411	pt.	±4%	5.9	6.9	7.7
Bulk	ISO 534 TAPPI T411	cm ³ /g	-	1.30	1.30	1.30
Opacity	ISO 2471 TAPPI T519	%	-2.0	95.0	96.0	97.5
Whiteness D65/10°	ISO 11475	CIE	±3	119	119	119
Relative humidity	TAPPI T502	%	±7	50	50	50

Values are subject to change without notice.

Last update: 03/03/2026