

Formula CF

Description:

Coated paper on the front side containing a layer of activated clay.

Colors available: White, yellow, blue, pink, green.

End uses:

Business forms, Invoices

Print methods:

Offset

Certificates:

- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [ISO 14001 Environment](#)
- [EMAS Leitza mill](#)
- [ISO 50001 Energy Efficiency](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety](#)

For applications that require specific certifications or approvals, please contact our sales teams.

Formula CF

Technical specifications

Property	Test Method	Unit	Tolerance	57	60	75	80	90	130	173
Substance	ISO 536	g/m ²	±4%	57	60	75	80	90	130	173
Thickness	ISO 534	μm	g≤130±4 g≥130±10	65	68	85	97	110	152	202
Opacity	ISO 2471	%	±4	80	81	84	88	91	93	97
Relative humidity	TAPPI T502 OM - 89	%	±5	43	43	43	43	43	43	43
Curl	TAPPI T427 UM- 85	mm	(4.0)-0.0	-2.0	-2.0	-2.0	-2.0	-2.0	-2.0	-2.0
Whiteness D65/10°	ISO 11475	° CIE	±6	118	118	118	113	113	124	124

GUARANTEES:

20 years legibility of the copy under normal conditions of storage (T: 15-25 °C and 50-60% RH).

5 years shelf life under normal conditions of storage and with the original packaging.

Values are subject to change without notice.

Last update: 01/29/2025