



PRODUCT SPECIFICATION
Index Board 190 g/m², coloured

Rev.: 9
Date: 2021-02-08
Ref.: KK

Characteristic	Unit	Mean	Tolerance	Testing Method
Substance	g/m ²	190	± 8	ISO 536
Caliper	g/m ²	220	± 10	ISO 534
Smoothness Bekk topside	µm	30	± 10	ISO 5627
Wax Test Dennison		> 14		T 459 OS - 75
Breaking length md	m	6000	± 1000	ISO 1924 - 1
Breaking length cd	m	3000	± 500	ISO 1924 - 1

subject to change without notice

Papierfabrik August Koehler SE

Hauptstraße 2 · D-77704 Oberkirch · Telefon +49 7802 81-0 · Fax +49 7802 81-4330 · www.koehlerpaper.com
Wer Kehl: Koehler Kehl GmbH · Bremenwörtstraße 4 · D-77694 Kehl · Telefon +49 7851 66-7000 · Fax +49 7851 66-7789

Sitz: D-77704 Oberkirch · Amtsgericht Freiburg i. Br. · HRB 709115
Vorstand: Kai Furler (Vorsitzender), Dr. Stefan Karrer, Frank Lendowski · Vorsitzender des Aufsichtsrats: Wolfgang Furler