

MM Kwidzyn sp. z o.o.
UL. LOTNICZA 1,
82-500 KWIDZYN, POLAND



TECHNICAL DATA SHEET

OPTIMAL

Parameter	Standard	Unit	Measurement
Substance	EN ISO 536	g/m²	60 ± 2
Thickness	ISO 534	µm	77 ± 3
Moisture content	EN ISO 287	%	6 ± 1
Whiteness	ISO 11475	CIE units	146 ± 3
Opacity	ISO 2471	%	85 +2/-1
Bendtsen roughness	ISO 8791-2	ml/min	160 ± 50
Cobb 60	EN ISO 535	g/m²	≤30
Tensile strength	EN ISO 1924-2	kN/m	4,0 +2/-1

AVAILABLE CERTIFICATION:



✓ 100% ECF fibres