

# Gloss 80 / SP123 / WK80

Facestock

## Gloss 80

Description Gloss coated woodfree paper.

Applications High resolution standard gloss label for multicolour printing. Extensively used in food and

beverage industry, logistics, stationery and cosmetics products.

Printing techniques Suitable for printing on flexo (all types), letterpress (conventional and UV), conventional offset, offset UV, screen printing, hot stamping, thermal transfer, laser.

Norm	Units	Value	Tolerance
ISO 536	g/m²	80	± 4%
ISO 534	μm	67	± 4%
ISO 5627	s	≥ 850	
ISO 2470-2	%	93	± 2
ISO 11475	%	117	±3
ISO 8254-1	%	66	± 5
ISO 2471	%	88,5	-2
ISO 1924-2	kN/m	4,4	-0,7
ISO 1924-2	kN/m	2.5	-0.3
	ISO 536 ISO 534 ISO 5627 ISO 2470-2 ISO 11475 ISO 8254-1 ISO 2471 ISO 1924-2	ISO 536 g/m² ISO 534 µm ISO 5627 s ISO 2470-2 % ISO 11475 % ISO 8254-1 % ISO 2471 % ISO 1924-2 kN/m	ISO 536 g/m² 80 ISO 534 μm 67 ISO 5627 s ≥ 850 ISO 2470-2 % 93 ISO 11475 % 117 ISO 8254-1 % 66 ISO 2471 % 88,5 ISO 1924-2 kN/m 4,4

Adhesive

**SP123** 

Description Acrylic super-permanent adhesive with high tack. For difficult surfaces such as wood, some cardboards and plastics such as HDPE, PP, PET and PVC.

Shelf life From the date of manufacture 2 years in 20°C and RH 50%

Property	Norm	Units	Value	Tolerance
Adhesion (Peel 180° 20'/stainless steel)	FTM 1	N/25mm	17,2	≥ 13,5
Tack (Quick Stick stainless steel)	FTM 9	N	11	≥ 9,8
Shear (1kg, in²/glass)	FTM 8	min	100	≥ 60
Minimum labelling temperature		°C	+5	
Minimum service temperature		°C	-20	
Maximum service temperature.		°C	+80	

Liner

## Kraft White 80

Description One-side coated white liner with good lay-flat characteristics. Suitable for sheeting. Available only in solid back

Color White

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m²	80	± 4%
Thickness	ISO 534	μm	81	± 4
Tensile strength MD/CD	ISO 1924-2	kN/m	4,6/2,3	-0,6/-0,3





## Certificates

Product approvals and usage certificates

Facestock

#### Gloss 80

Contact with foodstuff (BfR XXXVI) - Facestock and Liners (paper)

EN 1230 Sensorial analysis

Packaging and packaging waste Directive 94/62/CE

EN 71-3 Toy safety

Electric and electronic equipment (RoHS)

Adhesive

## **SP123**

Packaging and packaging waste Directive 94/62/CE

German Recommendation BfR XIV (ISEGA) - Adhesives

Liner

## Kraft White 80

Contact with foodstuff (BfR XXXVI) - Facestock and Liners (paper)

Packaging and packaging waste Directive 94/62/CE

EN 71-3 Toy safety

Electric and electronic equipment (RoHS)

For further details regarding compliance with food contact regulation, please contact our sales teams.

- Values are subject to change without notice. Last updated 3/15/2016.
- The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.



Our self-adhesive mill is certified to the strictest environmental standards ISO 14001 and EMAS and has successfully completed audits for ISO 50001, ISO 9001 and ISO 45001 certification. Adestor paper products are available with PEFC<sup>™</sup> and FSC® C011032 chain of custody certificates upon request.