



Report VNNF 082885.1

Test Report

Applicant

Europapier CE GmbH
Autokaderstraße 86-96
1210-Wien
Austria

Reference

Mrs. Nicole Messinger

Application

Determination of burning-, smoke- and dripping behavior according to ÖNORM A 3800 part 1.

Test material

Banner material "myMEDIA 3050 Frontlit Pro FR"

Material used in testing was anonymized for laboratory purposes. A detailed sample list is contained in the report.

Issuing and Signatures

Number of pages contained: 5
Original Issue / Vienna 05.04.2016 / tg / 1338
Translation / Vienna 21.06.2017 / da2

Authorised for Institute
Ing. Hannes Vittek

A handwritten signature in blue ink, reading "i.v. Zambach", written over a horizontal dotted line.

Contents

1 Order 2
 1.1 Chronology 2
 1.2 Samples 2
 2 Findings / Tests performed 3
 2.1 Description of the specimen 3
 2.2 Test and evaluation of burning behaviour excluding building products 3
 2.3 Test and evaluation of dropping behaviour 4
 2.4 Determination of smoke emission 4
 3 Remarks 5

1 Order

1.1 Chronology

Date	Received	Order
23.03.2016	24.03.2016	Determination of burning-, smoke- and dripping behavior according to ÖNORM A 3800 part 1.

1.2 Samples

Nr.	Received	Sample Identification
1	24.03.2016	"myMEDIA 3050 Frontlit Pro FR"

(Unless otherwise stated samples are provided by the customer.)

2 Findings / Tests performed

2.1 Description of the specimen

Description of the specimen according to DIN 60 000*

Test results

Tested sample: 1

Type of fibre according to DIN ISO 2076	Base fabric: Polyester Coating: PVC (declaration by the applicant)
Weight per unit area [g/m ²]	510 ± 10 (declaration by the applicant)
Print side	One-sided
Technological description	Coated woven fabric

2.2 Test and evaluation of burning behaviour excluding building products

Test conditions

Standard: ÖNORM A 3800-1 point 4.1

Arrangement of the sample: loose

Test results

Tested sample: 1

Evaluation criteria	Test		
	1	2	3
Ignition of the not flamed specimen [yes/no]	no	no	no
Afterflame time [min:sec]	0:00	0:00	0:00
Afterglow time [min:sec]	0:00	0:00	0:00
Undestroyed length of flamed specimen [cm]	46	49	49

Classification

According to the classification criteria of ÖNORM A 3800-1, point 4.1, the tested sample

can be classified as "Brennbarkeitsklasse - schwerbrennbar" ¹⁾

¹⁾ In the withdrawn standard ÖNORM B 3800-1:1988 classified as "Brennbarkeitsklasse B1-schwerbrennbar"

2.3 Test and evaluation of dropping behaviour

Test conditions

Standard: ÖNORM A 3800 part 1 item 4.3
Kind of flaming: Schlyterbrenner

Test results

Tested sample: 1

	dropping	number of drops falling down	kindling
Test 1	no	0	--
Test 2	no	0	--
Test 3	no	0	--

Classification

The tested specimen can be classified according to ÖNORM A 3800-1, item 4.3.1 as:

Tropfenbildungsklasse Tr 1 - nicht tropfend

2.4 Determination of smoke emission

Test conditions

Standard: ÖNORM A 3800 part 1/4.2
Arrangement of the specimen: loose

Test results

Tested sample: 1

smoke emission [%]					
Test 1	Test 2	Test 3	Test 4	Test 5	Mean Value
14	13	9	12	11	12

Classification

The tested specimen can be classified according to ÖNORM A 3800-1, item 4.2.1 as:

Qualmbildungsklasse Q1 - schwachqualmend

3 Remarks

Validity

There are no regulations concerning duration of validity in the individual test standards. As the results of the examinations refer only to the submitted and examined samples, the report is valid for these for an unlimited period. A period of validity specified as part of an expert evaluation is in the discretion of the consultant or the ÖTI.

The applicability of results and expert evaluations for materials not tested is in the responsibility of the applicant. Whereby an apportionment of results as well as any specified period of validity can only be done for identically constructed products and only as long as the product produced unchanged.

Possible national or international restrictions concerning the terms of usability of test and classification reports have to be considered; this is not the responsibility of the test laboratory.

Sample Material

Results of performed tests only refer to the sample material provided.

Without explicit written other agreement testing is destructive and the sample material is transferred to the property of ÖTI, which is entitled to freely decide on storage and disposal.

Issuance

The valid first issue is done in paper and has single-handed signatures. For reference purposes and filing an unsigned electronic duplicate can be delivered in pdf format. Duplicates and translations will be marked accordingly on the cover sheet.

Quality management, Accreditation and Notification

All tests and services are performed under a quality management system according to EN ISO/IEC 17025 respectively EN ISO/IEC 17065.

The ÖTI is accredited as Testing Laboratory and Certification Body for products. It also is a Notified Body for several directives with the registration number 0534 (see <http://ec.europa.eu/enterprise/newapproach/hando/>). Accreditation as Testing Laboratory was provided by Akkreditierung Austria (bmwfw). The scope of accreditation is listed on www.bmwfw.gv.at/akkreditierung.

In this report individual non-accredited test procedures are marked with *.

According to the decree on the use of the accreditation mark ("AkkZV") the accreditation mark is only to be used by the accredited Conformity Assessment Body.

Application of the registration number of the Notified Body: As to personal protective equipment (PPE) the requirements of PSA-SV § 10, BGBl. Nr. 596/1994 as amended and article 13 of the Directive 89/686/EEC have to be kept. With construction products the application is only permitted within the declaration of performance for CE-marking.

Copyright and Usage Notes

It is pointed out, that any alterations, amendments or falsifications of reports not authorized by the issuer of the report will be prosecuted as civil and criminal offences; this especially to the appropriate requirements of ABGB, UrhG, UWG and criminal law and their respective international equivalents.

Reports are protected under international copyright laws. Written consent of the ÖTI is required for publications (also in excerpt) and reference to tests for public relation purposes. Reports may only be reproduced in full length.

End of report